

(19) World Intellectual Property Organization  
International Bureau(43) International Publication Date  
20 July 2006 (20.07.2006)

PCT

(10) International Publication Number  
WO 2006/075822 A1

- (51) International Patent Classification:  
H05B 33/26 (2006.01)
- (21) International Application Number:  
PCT/KR2005/001001
- (22) International Filing Date: 7 April 2005 (07.04.2005)
- (25) Filing Language: Korean
- (26) Publication Language: English
- (30) Priority Data:  
10-2004-0024470 9 April 2004 (09.04.2004) KR
- (71) Applicant (for all designated States except US): LG  
CHEM, LTD. [KR/KR]; 20, Yoido-dong, Young-  
dangpo-gu, Seoul 150-721 (KR).
- (71) Applicant and
- (72) Inventor (for all designated States except US): NOH,  
Jeoung-Kwen [KR/KR]; 301-408 Geumhwa Maeul Ju-  
gong Green Villa, Sanggal-ri, Giheung-eup, Yongin-si,  
Gyeonggi-do 449-905 (KR).
- (72) Inventors; and
- (75) Inventors/Applicants (for US only): JEONG, Ji-Weon  
[KR/KR]; 104-1501 Sejong Apartment, Jeonmin-dong,  
yuseong-gu, Daejeon 305-390 (KR). LEE, Young-Chul

[KR/KR]; 101-405 Daerim Durae Apartment, Shin-  
sung-dong, Yuseong-gu, Daejeon 305-345 (KR). HAHM,  
Yun-Hye [KR/KR]; Ma-201, Wansung Villa, 10-5 Myeon-  
mok 8-dong, Jungnang-gu, Seoul 131-208 (KR). JEONG,  
Dong-Seob [KR/KR]; 3-514 LG Chemical Apartment,  
637, Doryong-dong, Yuseong-gu, Daejeon 305-340 (KR).  
JANG, Jun-Gi [KR/KR]; 7-401 LG Chemical Apartment,  
Doryong-dong, Yuseong-gu, Daejeon 305-340 (KR).


(74) Agent: HAM, Hyun-Kyung; 14F, Kukdong Building,  
60-1 Chungmuro3-ka, Chung-ku, Seoul 100-705 (KR).

(81) Designated States (unless otherwise indicated, for every  
kind of national protection available): AE, AG, AL, AM,  
AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN,  
CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI,  
GB, GD, GE, GH, GM, GR, HU, ID, IL, IN, IS, JP, KE,  
KG, KM, KN, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD,  
MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG,  
PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SM, SY,  
TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU,  
ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every  
kind of regional protection available): ARIPO (BW, GH,

(Continued on next page)

(54) Title: STACKED ORGANIC LIGHT EMITTING DEVICE HAVING HIGH EFFICIENCY AND HIGH BRIGHTNESS.



(57) Abstract: Disclosed is a stacked organic light emitting device and a display apparatus including the stacked organic light emitting device. The stacked organic light emitting device includes an anode connected to an external power source, a cathode connected to the external power source, at least two light emitting sections aligned between the anode and the cathode, including a light emitting layer, and an internal electrode aligned between the light emitting sections. The internal electrode is a single-layered internal electrode which is made from one selected from the group consisting of a metal, alloys of the metal, and metal oxides thereof, having a work function below 4.5 eV, each light emitting section includes an organic material layer containing an organic material having an electron affinity above 4 eV, and the organic material layer is formed between the light emitting layer of the light emitting section and the electrode facing the anode connected to the external power source in two electrodes which make contact with the light emitting section.



GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IS, IT, LI, LU, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

**Published:**

— with international search report

*For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.*

**STACKED ORGANIC LIGHT EMITTING DEVICE HAVING HIGH EFFICIENCY  
AND HIGH BRIGHTNESS**

**Technical Field**

5       The present invention relates to a stacked organic light emitting device. More particularly, the present invention relates to a stacked organic light emitting device including a single-layered internal electrode aligned between stacked light emitting sections.

10

**Background Art**

      An organic light emitting device is a semiconductor device for converting electric energy into optical energy. The organic light emitting device includes two opposite  
15    electrodes (an anode and a cathode) for applying external power to the organic light emitting device and an organic material layer aligned between the anode and the cathode in order to emit light having a wavelength of the visible ray range when a hole is recombined with an electron. As a  
20    forward electric field is applied to the organic light emitting device having the above structure, holes and electrons generated from the anode and cathode are injected into the organic material layer so that the holes are combined with the electrons in the organic material layer,  
25    thereby generating excitons. When the excitons have become the ground state, light is generated. Recently, an organic material layer with a multi-layered structure (see, Applied Physics Letters, vol. 51, no. 12, pp. 913-915, 1987) has been suggested in order to allow the holes and electrons generated  
30    from the electrodes of the organic light emitting device to

be effectively injected or transferred into the organic material layer. If the organic material layer is formed with the multi-layered structure, it is possible to drive the organic light emitting device with significantly reduced operational voltage while improving light emitting efficiency of the organic light emitting device.

In the meantime, various attempts have been made to realize high brightness in organic light emitting devices. For instance, a method of increasing current density obtained by applying an electric field to the organic light emitting device has been suggested. However, since an organic material layer and a thin film structure of the organic light emitting device are weak against heat, higher current density may exert a bad influence upon the organic material layer and the thin film structure of the organic light emitting device, so that the stability of the organic light emitting device may be degraded as the current density increases. For this reason, current studies are focused on organic light emitting devices representing high brightness at low current density.

There are two approaches to obtain high brightness at low current density. The first approach is to use an organic material capable of improving generation efficiency of excitons, which are generated due to recombination of holes and electrons, and/or generation efficiency of photons, which are generated when the excitons have become the ground state. The second approach is to stack at least two organic light emitting device units in series, in which each organic light emitting device unit includes an anode, a cathode and a light emitting section having a light emitting layer capable of emitting light by receiving holes and electrons from the

anode and the cathode, respectively. In the following description, a term "stacked organic light emitting device" refers to the structure including at least two organic light emitting device units stacked in series. The light emitting section may include an organic material layer having a multi-layered structure including a hole injection layer, a hole transport layer, a light emitting layer and an electron transport layer, if necessary.

Methods of fabricating the above-mentioned stacked organic light emitting devices have been disclosed in various documents.

For instance, International Publication No. WO95/06400 discloses a stacked organic light emitting device including organic light emitting device units capable of emitting lights having different wavelengths such that light with desired colors can be emitted from the stacked organic light emitting device. According to the above stacked organic light emitting device, each organic light emitting device unit includes two electrodes and a light emitting layer aligned between two electrodes. In addition, the electrodes are connected to the external power source, respectively, in such a manner that the organic light emitting device units can be individually driven.

In addition, International Publication No. WO99/03158 discloses a stacked organic light emitting device including organic light emitting device units capable of emitting lights having the same wavelength such that light with improved brightness can be emitted from the stacked organic light emitting device. The stacked organic light emitting device disclosed in International Publication No. WO99/03158

has a structure similar to that of the stacked organic light emitting device disclosed in International Publication No. WO95/06400, except that the external power source is connected to both ends of the stacked organic light emitting device. That is, external electrodes of the stacked organic light emitting device are connected to the external power source and internal electrodes of the stacked organic light emitting device are disconnected from the external power source.

10 According to the above-mentioned stacked organic light emitting devices, internal electrodes interposed between the organic light emitting device units include an internal anode in the form of a conductive thin film electrode made from indium-tin-oxide (ITO) or Au having a high work function, and  
15 an internal cathode in the form of a metal thin film electrode made from Al (4.28 eV), Ag (4.26 eV), or Ca (2.87 eV). Thus, two-layered internal electrodes, that is, the internal anode and the internal cathode are aligned between the organic light emitting device units of the stacked  
20 organic light emitting device while making contact with each other. FIG. 1 shows such a stacked organic light emitting device including two-layered internal electrodes between the organic light emitting device units.

However, according to the stacked organic light emitting  
25 device having the structure as shown in FIG. 1, since an ITO-based transparent oxide electrode (internal anode) is formed on a metal thin film (internal cathode), to which electrons are injected, a physical bonding property between the internal anode and the internal cathode is degraded, so the  
30 two-layered internal electrodes cannot be effectively formed.

In addition, if the internal anode is made from ITO, a sputtering process must be carried out due to the characteristics of the ITO. However, such a sputtering process may increase kinetic energy of atoms ( $< \text{KeV}$ ) as compared with that of an evaporation process ( $< \text{leV}$ ). For this reason, if the internal anode is formed through the sputtering process by using ITO, an organic semiconductor thin film already formed may be significantly damaged (see, Journal of Applied Physics, vol. 86, no. 8, pp. 4607-4612, 1999).

In the meantime, European Patent Publication No. 1351558 A1 discloses a stacked organic light emitting device including a single-layered internal electrode made from a single non-conductor thin film having specific resistance above  $10^5 \Omega\text{cm}$  without forming two-layered internal electrodes between stacked light emitting sections. The single non-conductor thin film is made from a material capable of simultaneously generating holes and electrons as an electric field is applied to the stacked organic light emitting device in such a manner that the holes and electrons are injected into a hole transport layer and an electron transport layer, respectively. However, the single non-conductor thin film is very expensive and a method of forming the single non-conductor thin film is very difficult.

Accordingly, it is necessary to provide a stacked organic light emitting device, which can be easily fabricated without forming two-layered internal electrodes between stacked light emitting sections.

#### Brief Description of the Drawings

FIG. 1 is a view illustrating a structure of a conventional stacked organic light emitting device including two-layered internal electrodes formed between stacked light emitting sections.

5           FIG. 2 is a view illustrating a structure of a stacked organic light emitting device including a single-layered internal electrode formed between stacked light emitting sections according to one embodiment of the present invention, wherein reference numerals 1 to 10 represent a  
10 stacked organic light emitting device, a glass substrate, an external anode, a first light emitting section, an internal electrode, a second light emitting section, an external cathode, first and second organic light emitting units and an external power sources, respectively.

15           FIG. 3 is a view illustrating energy levels of organic material layers and internal electrode material formed in an organic light emitting device unit of a stacked organic light emitting device using a single-layered internal electrode according to one embodiment of the present invention.

20           FIG. 4 is a graph illustrating UPS (ultraviolet photoelectron spectroscopy) data generated from a gold film and a HAT film formed on the gold film with a thickness of about 20nm according to Reference Example 1.

25           FIG. 5 is a graph illustrating a UV-VIS spectrum obtained from HAT organic material deposited on a glass surface according to Reference Example 1.

          FIG. 6 is a view illustrating a structure of a single organic light emitting device according to Comparative Example 1.

30           FIG. 7 is a view illustrating a structure of an organic



light emitting device according to Comparative Example 2, in which the organic light emitting device includes two-layered light emitting sections without forming an internal electrode therebetween.

5        FIG. 8 is a view illustrating a structure of a stacked organic light emitting device according to Example 1, in which a single-layered internal electrode is formed between two-layered light emitting sections.

10        **Disclosure of the Invention**

Inventors of the present invention have found that, in a stacked organic light emitting device including an anode connected to an external power source, a cathode connected to the external power source, at least two light emitting sections including a light emitting layer aligned between the anode and the cathode, and an internal electrode aligned between the light emitting sections, if an organic material layer containing an organic material having an electron affinity above 4 eV is formed between the light emitting layer of the light emitting section and the internal electrode facing the anode connected to the external power source in two internal electrode which make contact with the light emitting section, it is possible to fabricate the internal electrode by using a single-layered internal electrode made from one selected from the group consisting of a metal, alloys of the metal, and metal oxides thereof, having a work function below 4.5 eV.

Accordingly, it is an object of the present invention to provide a stacked organic light emitting device including a single-layered internal electrode aligned between stacked

30

light emitting sections.

The present invention provides a stacked organic light emitting device comprising: an anode connected to an external power source; a cathode connected to the external power source; at least two light emitting sections aligned between the anode and the cathode, including a light emitting layer; and an internal electrode aligned between the light emitting sections, wherein the internal electrode is a single-layered internal electrode which is made from one selected from the group consisting of a metal, alloys of the metal, and metal oxides thereof, having a work function below 4.5 eV, each light emitting section includes an organic material layer containing an organic material having an electron affinity above 4 eV, and the organic material layer is formed between the light emitting layer of the light emitting section and the electrode facing the anode connected to the external power source in two electrodes which make contact with the light emitting section.

A structure of the stacked organic light emitting device according to the present invention is shown in FIG. 2.

In addition, the present invention provides a display apparatus including the stacked organic light emitting device.

Definitions of terms used in the following description are as follows:

The light emitting section means an organic material layer unit, which is aligned between an anode and a cathode in a single organic light emitting device and includes a light emitting layer capable of emitting light by receiving holes and electrons from the anode and the cathode,

respectively. The organic material layer unit is different from the organic light emitting device unit including the electrodes and the light emitting section. The light emitting section can be provided in the form of a single organic  
5 material layer acting as a light emitting layer or in the form of a multiple organic material layer including a hole injection layer, a hole transport layer, a light emitting layer, and an electron transport layer.

The internal electrode means an electrode positioned  
10 between the light emitting sections in the stacked organic light emitting device. The internal electrode is different from the external electrode positioned at an outermost portion of the stacked organic light emitting device.

The stacked organic light emitting device means a  
15 stacked structure of single organic light emitting device units including an anode connected to an external power source, a cathode connected to the external power source, at least two light emitting sections aligned between the anode and the cathode and including light emitting layers, and an  
20 internal electrode formed between the stacked light emitting sections.

In addition, "HOMO" is an abbreviation of "the highest occupied molecular orbital" and "LUMO" is an abbreviation of "the lowest unoccupied molecular orbital".

25

#### **Best Mode for Carrying Out the Invention**

Hereinafter, the present invention will be described in detail.

30 In a conventional stacked organic light emitting device,

two-layered internal electrodes including an internal anode and an internal cathode, which make contact with each other, are formed between the stacked light emitting sections. In such a conventional stacked organic light emitting device, a material having a relatively high work function is used for the internal anode for the purpose of hole injection and a material having a relatively low work function is used for the internal cathode for the purpose of electron injection.

However, inventors of the present invention have found that, if an organic material layer containing an organic material having an electron affinity above 4 eV is formed in the light emitting section between the light emitting layer of the light emitting section and the electrode facing the external anode in two electrodes which make contact with the light emitting section, it is possible to fabricate the internal electrode by using a single-layered internal electrode made from one selected from the group consisting of a metal, alloys of the metal, and metal oxides thereof, having a work function below 4.5 eV.

Hereinafter, an operational principle of the present invention will be described with reference to FIG. 3.

In the present invention, a term "electron affinity" means a difference between a vacuum level and a LUMO energy level. The LUMO energy level can be calculated by adding an optical band gap to a HOMO energy level, wherein the HOMO energy level can be obtained by measuring ionization potential.

If an organic material layer containing an organic material having the electron affinity above 4 eV is formed in the light emitting section between the light emitting layer

of the light emitting section and the electrode facing the external anode in two electrodes which make contact with the light emitting section, there is no great difference between the LUMO energy level of the organic material layer and the HOMO energy level of the hole transport layer or the light emitting layer in the light emitting section to which the organic material layer is adjacent (the HOMO energy level of the existing hole transport layer is set to 5.0-6.0 eV). In addition, if the organic material layer has the electron affinity above 4 eV, electrons in the HOMO energy level of the hole transport layer or the light emitting layer can be easily transferred to the organic material layer. At this time, if the electrons in the HOMO energy level of the hole transport layer or the light emitting layer are emitted, holes are generated at the very electron emitted site, i.e., in the HOMO energy level of the hole transport layer or the light emitting layer. The holes in the HOMO energy level may move to the light emitting layer through the HOMO energy level, if necessary. Accordingly, when the organic material layer is formed with an organic material having the electron affinity above 4 eV, the organic material layer may act as an anode and/or a hole injection layer. In addition, the electrons shifted into the LUMO energy level of the organic material layer having the electron affinity above 4 eV can move between molecules and have an electric conductive characteristic, so that the electrons may move toward an electrode facing the external anode due to an electric potential between the external anode and the external cathode connected to the external power source.

The reason for setting the electron affinity above 4 eV


is to receive electrons from the hole transport layer or the light emitting layer positioned adjacent to the organic material layer having the electron affinity above 4 eV while injecting holes into the hole transport layer or the light emitting layer and to easily inject electrons into a metal internal electrode.

Preferably, the organic material having a high electron affinity above 4 eV ensures high carrier mobility. In this case, threshold voltage and driving voltage of the device can be lowered.

According to the operational principle as mentioned above, the organic material layer having the electron affinity above 4 eV, which is formed between the light emitting layer of the light emitting section and the electrode facing the external anode in two electrodes which make contact with the light emitting section, can act as an anode. Therefore, according to the stacked organic light emitting device of the present invention, it is possible to form a single-layered internal electrode by using a metal, alloys of the metal, or metal oxides thereof, having a work function below 4.5 eV, which are known as materials for the cathode of the organic light emitting device used for injecting electrons into the organic material layer of the organic light emitting device when external power is applied thereto, without forming a separate internal anode between the light emitting sections of the stacked organic light emitting device.

An example of the organic material having the electron affinity above 4 eV is shown in chemical formula 1.

Chemical Formula 1



In above chemical formula 1,  $R_1$  to  $R_6$  are one selected  
 5 from the group consisting of hydrogen, halogen atom, nitrile  
 ( $-\text{CN}$ ), nitro ( $-\text{NO}_2$ ), sulfonyl ( $-\text{SO}_2\text{R}$ ), sulfoxide ( $-\text{SOR}$ ),  
 sulfonamide ( $-\text{SO}_2\text{NR}_2$ ), sulfonate ( $-\text{SO}_3\text{R}$ ), trifluoromethyl ( $-\text{CF}_3$ ),  
 ester ( $-\text{COOR}$ ), amide ( $-\text{CONHR}$  or  $-\text{CONRR}'$ ), substituted  
 or unsubstituted linear or branched  $\text{C}_1\text{-C}_{12}$  alkoxy, substituted  
 10 or unsubstituted linear or branched  $\text{C}_1\text{-C}_{12}$  alkyl, substituted  
 or unsubstituted aromatic or non-aromatic heterocyclic  
 compound, substituted or unsubstituted aryl, substituted or  
 unsubstituted mono-arylamine or di-arylamine, and substituted  
 or unsubstituted aralkyl. In addition,  $R$  and  $R'$  are one  
 15 selected from the group consisting of substituted or  
 unsubstituted  $\text{C}_1\text{-C}_{60}$  alkyl, substituted or unsubstituted aryl,  
 and substituted or unsubstituted 5-7 membered heterocyclic  
 compound.

$\text{C}_1\text{-C}_{60}$  alkyl, aryl and heterocyclic compound of  $R$  and  $R'$   
 20 can be substituted with at least one functional group, which  
 is one selected from the group consisting of amine, amide,  
 ether, and ester radicals.

In addition, aryl is one selected from the group  
 consisting of phenyl, biphenyl, terphenyl, benzyl, naphthyl,

anthracenyl, tetracenyl, pentacenyl, perylenyl, and coronenyl, which can be mono-substituted, poly-substituted or unsubstituted.

If an electron withdrawing functional group (hydrogen, halogen atom, nitrile (-CN), nitro (-NO<sub>2</sub>), sulfonyl (-SO<sub>2</sub>R), sulfoxide (-SOR), sulfonamide (-SO<sub>2</sub>NR<sub>2</sub>), sulfonate (-SO<sub>3</sub>R), trifluoromethyl (-CF<sub>3</sub>), ester(-COOR), amide (-CONHR or -CONRR') is applied to R<sub>1</sub> to R<sub>6</sub>, the electrons introduced into  $\pi$ -orbital of a core structure shown in chemical formula 1 are withdrawn by means of the electron withdrawing function group so that the electrons are stabilized, i.e., re-localized, thereby leveling up the electron affinity, that is, a LUMO level may drop down.

According to the present invention, it is preferred to use -CN for R<sub>1</sub> to R<sub>6</sub>.

Examples and synthesis methods for above chemical formula 1 are disclosed in Korean Patent Application No. 10-2003-87159 in detail, the contents of which are incorporated herein by reference.

Another example of the organic material having the electron affinity above 4 eV includes 2,3,5,6-tetrafluoro-7,7,8,8-tetracyanoquinodimethane (F4TCNQ, LUMO energy level = 5.24 eV), fluoride 3,4,9,10-perylenetetracarboxylicdianhydride (PTCDA), cyano PTCDA, naphthalenetetracarboxylicdianhydride (NTCDA), fluoride NTCDA and cyano NTCDA.

According to the present invention, the single-layered internal electrode is made from one selected from the group consisting of a metal having a work function below 4.5 eV, preferably below 4.3 eV, more preferably in a range of 3.5 eV



to 4.3 eV, alloys of the metal, and metal oxides thereof. Since the single-layered internal electrode can be made from materials having a low work function, electrons are effective injected if the single-layered internal electrode is used as  
5 a cathode for the organic light emitting device.

In addition, since the metal having the work function below 4.5 eV used for the internal electrode can be melted by means of heat, the internal electrode can be formed through a thermal evaporation process instead of a sputtering process.  
10 Thus, the stacked organic light emitting device can be prevented from being damaged and a process cost can be reduced. However, all metal alloy or metal oxide having the work function below 4.5 eV is not adaptable to the thermal evaporation process. If the metal alloy or metal oxide has a  
15 high melting point, an e-beam evaporation process or a sputtering process is carried out.

The metal used for fabricating the single-layered internal electrode includes Al (4.28 eV), Ag (4.26 eV), Zn (4.33 eV), Nb (4.3 eV), Zr (4.05 eV), Sn (4.42 eV), Ta (4.25  
20 eV), V (4.3 eV), Hg (4.49 eV), Ga (4.2 eV), In (4.12 eV), Cd (4.22 eV), B (4.4 eV), Hf (3.9 eV), La (3.5 eV), Ti (4.3 eV), a Nd or Pd alloy thereof, Ca (2.87 eV), Mg (3.66 eV), Li (2.9eV), Na (2.75eV), K (2.3eV), Cs, (2.14eV), or alloys thereof. However, the present invention is not limited to the  
25 above materials. Preferably, the single-layered internal electrode is made from one selected from the group consisting of Al (4.28 eV), Ag (4.26 eV) and alloys thereof.

The thickness of the single-layered internal electrode can be adjusted by taking transmittance of light having a  
30 wavelength of a visible ray range and electric conductivity

into consideration. In detail, the single-layered internal electrode must represent superior transmittance for the light in the visible ray range in order to allow the light generated from the light emitting device to be easily emitted to an exterior. To this end, it is preferred for the internal electrode to have a thin thickness as possible. However, a thin film made from a metal may represent low electric conductivity even if the metal has superior electric conductivity. Therefore, it is necessary to adjust the thickness of the internal electrode in such a manner that the internal electrode has superior electric conductivity while representing superior transmittance for the light. According to the present invention, the thickness of the internal electrode is preferably adjusted in a range of about 1 to 100Å.

According to the present invention, if the light emitting section aligned adjacent to the external anode includes the organic material layer containing the organic material having the electron affinity above 4 eV between the light emitting layer of the light emitting section and the external anode, the external anode can be fabricated by using a material having a relatively low work function as used for the internal electrode, as well as a material having a relatively high work function used for the anode of the conventional organic light emitting device. Therefore, the external anode can be fabricated not only using materials used for the internal electrode, but also using a metal having a high work function, such as V, Cr, Cu, Zn, Au or an alloy thereof, metal oxides, such as Zn oxide, In oxide, ITO (indium-tin-oxide) or In-Zn oxide, a combination of a metal

and oxide, such as ZnO:Al or SnO<sub>2</sub>:Sb, and conductive polymer, such as poly(3-methylthiophene), poly[3,4-(ethylene-1,2-dioxy)thiophene] (PEDT), polypyrrole, or polyaniline. However, the present invention is not limited to the above materials.

According to the present invention, the external cathode can be fabricated by using a material having a relatively low work function in such a manner that electrons can be easily injected into the organic material layer. In detail, the external cathode can be fabricated not only using materials used for the internal electrode, but also using a metal, such as Mg, Ca, Na, Yt, Li, Gd, Pb or an alloy thereof, and a multi-layered material, such as LiF/Al or LiO<sub>2</sub>/Al. However, the present invention is not limited to the above materials.

The stacked organic light emitting device according to one embodiment of the present invention can be fabricated through the following processes. The structure of the stacked organic light emitting device fabricated according to one embodiment of the present invention is shown in FIG. 2. As shown in FIG. 2, an anode 3 made from one of the above-mentioned anode materials is formed on a transparent glass substrate 2. Then, a first light emitting section 4 including a light emitting layer is formed on the anode 3. The light emitting section 4 can be fabricated with a multi-layered structure or a single-layered structure. The multi-layered structure may include a hole injection layer, a hole transport layer, a light emitting layer and an electron transport layer. According to the present invention, the light emitting section includes an organic material layer containing an organic material having an electron affinity

above 4 eV formed between the light emitting layer of the light emitting section and the electrode facing the external anode in two electrodes which make contact with the light emitting section. As mentioned above, the organic material layer containing the organic material having the electron affinity above 4 eV plays a role of a hole injection layer or a hole transport layer. In addition, the organic material layer can be used for the purpose of hole injection and hole transportation. Then, an internal electrode 5 having a thickness in a range of about a few Å to tens of Å is formed on the light emitting section 4 by using one of the above-mentioned materials. In addition, a second light emitting section 6 is formed on the internal electrode in the same manner as the first light emitting section 4. At this time, the internal electrode and the light emitting sections can be repeatedly formed by several times, if necessary. Finally, a cathode 7 is formed on the second light emitting section 6 by using one of one of the above-mentioned cathode materials. Herein, the electrode and the light emitting section including an organic material layer can be formed through a conventional technology generally known in the art.

The stacked light emitting sections are formed in the same structure by using the same material. However, it is also possible to form the stacked light emitting sections in different structures or by using different materials.

The stacked organic light emitting device of the present invention can be fabricated in the form of a top emission type organic light emitting device, a bottom emission type organic light emitting device, or a dual emission type organic light emitting device according to materials used for

the stacked organic light emitting device.

In addition, a display apparatus including the stacked organic light emitting device of the present invention can be fabricated through a conventional method generally known in the art.

Since the organic light emitting device units are connected to each other in series in the stacked organic light emitting device of the present invention, density of photons generated from the light emitting layer of each light emitting section may increase under the same current density, so that emission efficiency and brightness of light can be improved proportionally to the number of stacked light emitting sections.

In addition, according to the stacked organic light emitting device of the present invention, the light emitting section is fabricated in such a manner that it has a light emission spectrum of a color selected from red, green, blue, and a combination thereof. Thus, a light emitting device capable of emitting light having a white color or a desired color can be obtained by stacking the light emitting sections.

In the meantime, if the thickness of the light emitting section provided in the stacked organic light emitting device according to the present invention is properly adjusted, at least two overlapped optical peaks can be generated due to micro-cavity effect, so that a white light of a wide range can be produced, although it does not precisely match with the white light defined in a CRI (color rendition index). That is, if an internal electrode having a high reflective property is used, some of light generated from the light

emitting section is reflected from the internal electrode without being emitted to the exterior, thereby causing light interference in the stacked organic light emitting device. In this state, if the thickness of the organic material layer  
5 provided in the light emitting section is properly adjusted, a light emitting spectrum is changed, which is called "micro-cavity effect".

In addition, since the present invention employs a single-layered internal electrode, the problem occurring in  
10 the conventional stacked organic light emitting device in relation to two-layered internal electrodes, such as poor physical bonding force between internal electrodes, may not happen. Conventionally, the organic light emitting device is easily damaged when fabricating the internal anode through  
15 the sputtering process. However, the single-layered internal electrode of the present invention can be made from a material adaptable for the evaporation process, so the stacked organic light emitting device of the present invention can be prevented from being damaged, thereby  
20 improving stability of the stacked organic light emitting device. In addition, since the present invention employs the single-layered internal electrode, the present invention represents advantages in view of the manufacturing cost and manufacturing process as compared with the conventional art  
25 employing two-layered internal electrodes, which must be bonded to each other.

Hereinafter, embodiments of the present invention will be described in detail. It should be noted that the following  
embodiments are for illustrative purposes only and are not  
30 intended to limit the scope of the present invention.

## Embodiments

Reference Example 1: HOMO and LUMO levels of HAT (USP and UV-VIS absorption schemes)

5        In order to detect the HOMO level of Hexanitride hexaazatriphenylene (HAT), a UPS (Ultraviolet photoelectron spectroscopy) scheme was used. According to the UPS scheme, kinetic energy of the electrons emitted from a sample was analyzed while radiating vacuum UV line (21.20 eV) generated  
10 from a helium lamp onto the sample under an ultra high vacuum state ( $<10^{-8}$  Torr), thereby detecting the work function of the metals and ionization energy of organic materials, that is the HOMO level and the Fermi energy level. When the vacuum UV line (21.20 eV) radiates onto the sample, the kinetic energy  
15 of the electrons emitted from the sample corresponds to a difference between vacuum UV energy (21.20 eV) and electron binding energy of the sample to be measured. Accordingly, the binding energy distribution of materials in the sample can be detected by analyzing the distribution of the kinetic energy  
20 of the electrons emitted from the sample. If the kinetic energy of the electron represents a maximum value, the binding energy of the sample represents a minimum value. Thus, the work function (Fermi energy level) and the HOMO level of the sample can be determined.

25        In the reference example 1, after obtaining the work function of gold by using a gold film, the kinetic energy of the electrons emitted from a HAT film was analyzed while depositing the HAT film on the gold film, in order to obtain the HOMO level of the HAT. FIG. 4 shows UPS data generated  
30 from the gold film and the HAT film formed on the gold film

with a thickness of about 20nm. Hereinafter, the description will be made with reference to terminology disclosed in a document (H. Ishii, et al, Advanced Materials, 11, 605-625 (1999)). Binding energy shown in an x-axis of FIG. 7 was

5 calculated based on the work function measured from the metal film. That is, the work function of gold in reference example 1 can be obtained by subtracting a maximum value (15.92 eV) of the binding energy from vacuum UV line (21.20 eV). According to reference example 1, the work function of gold

10 was 5.28 eV. In addition, the HOMO level of the HAT can be obtained by subtracting a difference value between the maximum value (15.19 eV) and the minimum value (3.79) of the binding energy from the vacuum UV line (21.20 eV) radiated on the HAT deposited on the gold film. According to reference

15 example 1, the HOMO level of the HAT was 9.80 eV and the Fermi level was 6.02 eV.

An UV-VIS spectrum as shown in FIG. 5 was obtained by using an organic material formed by depositing the HAT on a surface of glass. In addition, a band gap of 3.26 eV was

20 obtained by analyzing an absorption edge. Thus, it is understood that the LUMO of the HAT is below 6.54 eV. The above value may vary according to exciton binding energy of the HAT film. That is, since 6.54 eV is larger than the Fermi level (6.02 eV) of the HAT film, the exciton binding energy

25 of the HAT film must exceed 0.52 eV in order to set the LUMO level lower than the Fermi level. In general, the exciton binding energy of the organic material is 0.52 eV (maximum value thereof is lower than 1 eV), so the LUMO level of the HAT is in the range of 5.54 to 6.02 eV.



## Comparative Example 1

A single organic light emitting device including a single organic light emitting section is fabricated as follows:


## 5 (1) Forming of Anode

A transparent anode having a thickness of about 1500 Å was formed on a transparent glass substrate by using ITO (indium-tin-oxide) through a sputtering process. Then, the transparent anode was subject to a plasma process by using  
10 forming gas, which was obtained by adding 4% of H<sub>2</sub> to Ar.

## (2) Forming of Light emitting section

Hexanitride hexaazatriphenylene (HAT) as shown in chemical formula 1a was deposited on the transparent anode through a vacuum deposition process, thereby forming a hole  
15 injection layer having a thickness of about 500 Å.


Chemical Formula 1a



20 After that, NPB was deposited on the hole injection layer through a vacuum deposition process, thereby forming a hole transport layer having a thickness of about 400 Å. Then, Alq3 doped with 1% of dopant (C545T) available from Kodak company was deposited on the hole transport layer through a

vacuum deposition process, thereby forming a light emitting layer having a thickness of about 300Å. After that, a compound as shown in chemical formula 2, which is disclosed in Korean Patent Application No. 10-2002-3025, was deposited on the light emitting layer through a vacuum deposition process, thereby forming an electron transport layer having a thickness of about 200Å.

Chemical Formula 2



10

## (3) Forming of Cathode

LiF and Al were sequentially deposited on the electron transport layer through an evaporation process, thereby forming a cathode.

15 A structure of an organic light emitting device fabricated through the above processes is shown in FIG. 6.

## Comparative Example 2

20 According to comparative example 2, the organic light emitting device was fabricated by performing the process identical to that of comparative example 1, except that the process for forming the light emitting section was repeated by two times. Therefore, the stacked organic light emitting

device included two light emitting sections without forming an internal electrode (an internal cathode (Al) and an internal anode (ITO)). A structure of the stacked organic light emitting device fabricated through the above processes is shown in FIG. 7.

#### Comparative Example 3

According to comparative example 3, the organic light emitting device was fabricated by performing the process identical to that of comparative example 1, except that the process for forming the organic light emitting section was repeated by two times, in which a single layered internal electrode having a thickness of about 60Å was formed by using Al after forming a first light emitting section, and then, a second light emitting section was formed without forming a HAT organic material layer. Thus, the organic light emitting device of comparative example 3 included two light emitting sections and an internal electrode made from Al interposed between two light emitting sections, in which the internal electrode did not include an internal anode (ITO) and the HAT organic material layer was omitted from the second light emitting section. A structure of the stacked organic light emitting device fabricated through the above processes is shown in FIG. 8.

25

#### Example 1

According to example 1, the organic light emitting device was fabricated by performing the process identical to that of comparative example 1, except that a single layered internal electrode having a thickness of about 60Å was formed

by using Al after forming a first light emitting section, and then, a second light emitting section was formed. Thus, the organic light emitting device of example 1 included two light emitting sections and an internal electrode made from Al interposed between two light emitting sections, in which the second light emitting section had a HAT organic material layer. A structure of the stacked organic light emitting device fabricated through the above processes is shown in FIG. 8.

10

#### Test Result

In a case of the single organic light emitting device of comparative example 1, current density of  $10 \text{ mA/cm}^2$  was represented under applied voltage of 3.9V. At this time, a light emitting efficiency was  $7.9 \text{ cd/A}$ , and brightness was  $790 \text{ cd/m}^2$ . In a case of the stacked organic light emitting device of comparative example 2, which does not include the internal electrode, current density of  $10 \text{ mA/cm}^2$  was represented under applied voltage of 8.7V. At this time, a light emitting efficiency was  $7.4 \text{ cd/A}$ , and brightness was  $742 \text{ cd/m}^2$ . In a case of the stacked organic light emitting device of comparative example 3, in which the second light emitting section did not include the HAT organic material layer, current density of  $10 \text{ mA/cm}^2$  was represented under applied voltage of 16.5V. At this time, a light emitting efficiency was  $5 \text{ cd/A}$ , and brightness was  $500 \text{ cd/m}^2$ . In addition, in a case of the stacked organic light emitting device of example 1, similarly to comparative example 2, current density of  $10 \text{ mA/cm}^2$  was represented under applied voltage of 8.7V. At this time, a light emitting efficiency

was 13.8 cd/A, and brightness was 1380 cd/m<sup>2</sup>. Table 1 shows the above test result.

Table 1

5

	Current density	Applied voltage	Light emitting efficiency	Brightness
Comparative example 1	10 mA/cm <sup>2</sup>	3.9 V	7.9 cd/A	790 cd/m <sup>2</sup>
Comparative example 2	10 mA/cm <sup>2</sup>	8.7 V	7.4 cd/A	742 cd/m <sup>2</sup>
Comparative example 3	10 mA/cm <sup>2</sup>	16.5 V	5 cd/A	500 cd/m <sup>2</sup>
Example 1	10 mA/cm <sup>2</sup>	8.7 V	13.8 cd/A	1380 cd/m <sup>2</sup>

In the case of the organic light emitting device of comparative example 2, in which the thickness of the stacked light emitting sections was enlarged by two times as compared with that of the comparative example 1 because the light emitting sections were stacked without forming the internal electrode therebetween, although applied voltage thereof was increased by approximately two times as compared with that of comparative example 1 in order to obtain the same current density thereof as that of comparative example 1, the light emitting efficiency and brightness thereof were similar to those of comparative example 1. It can be understood from the above result that, if the thickness of the organic material layer of the organic light emitting device is simply enlarged, the driving voltage must be increased in order to obtain the same current density, light emitting efficiency and brightness.

The light emitting efficiency and brightness of the stacked organic light emitting device according to example 1 were increased by two times as compared with those of the single light emitting device of comparative example 1 and the stacked organic light emitting device of comparative example 1, which did not include the internal electrode. In addition, when comparing example 1 with comparative example 3, it can be understood that the driving voltage is lowered and the light emitting efficiency and brightness are improved if the organic material layer having the electron affinity above 4 eV is interposed between the internal electrode and the light emitting layer, even if the internal electrode includes only the internal cathode without the internal anode. In addition, it can be understood from the above result that the single layered internal electrode interposed between the two light emitting sections and the organic material layer having the electron affinity above 4 eV may act as the internal anode and the internal cathode with respect to each of the stacked light emitting sections. That is, the single layered internal electrode and the organic material layer having the electron affinity above 4 eV may act as the hole injection layer and the electron injection layer.

#### 25 Industrial Applicability

As described above, according to the stacked organic light emitting device of the present invention, the light emitting efficiency and brightness are improved proportionally to the number of stacked light emitting sections, and desired light can be emitted according to wavelengths of the light

emitting sections. In addition, since the stacked organic light emitting device of the present invention includes the single layered internal electrode, the stacked organic light emitting device of the present invention can be easily  
5 fabricated at a low cost as compared with the conventional organic light emitting device having the two-layered internal electrodes. Furthermore, since it is not necessary to use materials adaptable for the sputtering process when forming the internal electrode, the stability of the stacked organic  
10 light emitting device according to the present invention can be improved.

### Claims

1. A stacked organic light emitting device comprising:

an anode connected to an external power source;

5 a cathode connected to the external power source;

at least two light emitting sections aligned between the anode and the cathode, including a light emitting layer; and

an internal electrode aligned between the light emitting sections, wherein


10 the internal electrode is a single-layered internal electrode which is made from one selected from the group consisting of a metal, alloys of the metal, and metal oxides thereof, having a work function below 4.5 eV,

each light emitting section includes an organic material  
15 layer containing an organic material having an electron affinity above 4 eV, and

the organic material layer is formed between the light emitting layer of the light emitting section and the electrode facing the anode connected to the external power  
20 source in two electrodes which make contact with the light emitting section.

2. The stacked organic light emitting device as claimed in claim 1, wherein the organic material having the  
25 electron affinity above 4 eV is a compound having a chemical formula as shown below.





wherein,  $R_1$  to  $R_6$  are one selected from the group consisting of hydrogen, halogen atom, nitrile ( $-\text{CN}$ ), nitro ( $-\text{NO}_2$ ), sulfonyl ( $-\text{SO}_2\text{R}$ ), sulfoxide ( $-\text{SOR}$ ), sulfonamide ( $-\text{SO}_2\text{NR}_2$ ), sulfonate ( $-\text{SO}_3\text{R}$ ), trifluoromethyl ( $-\text{CF}_3$ ), ester ( $-\text{COOR}$ ), amide ( $-\text{CONHR}$  or  $-\text{CONRR}'$ ), substituted or unsubstituted linear or branched  $\text{C}_1\text{-C}_{12}$  alkoxy, substituted or unsubstituted linear or branched  $\text{C}_1\text{-C}_{12}$  alkyl, substituted or unsubstituted aromatic or non-aromatic heterocyclic compound, substituted or unsubstituted aryl, substituted or unsubstituted mono-arylamine or de-arylamine, and substituted or unsubstituted aralkyl, and  $R$  and  $R'$  are one selected from the group consisting of substituted or unsubstituted  $\text{C}_1\text{-C}_{60}$  alkyl, substituted or unsubstituted aryl, and substituted or unsubstituted 5-7 membered heterocyclic compound.

3. The stacked organic light emitting device as claimed in claim 2, wherein  $R_1$  to  $R_6$  are nitrile ( $-\text{CN}$ ).

4. The stacked organic light emitting device as claimed in claim 1, wherein the organic material having the electron affinity above 4 eV is one selected from the group consisting of 2,3,5,6-tetrafluoro-7,7,8,8-

tetracyanoquinodimethane, fluoride 3,4,9,10-  
perylene-tetracarboxylic dianhydride (PTCDA), cyano PTCDA,  
naphthalene-tetracarboxylic dianhydride (NTCDA), fluoride NTCDA  
and cyano NTCDA.

5

5. The stacked organic light emitting device as  
claimed in claim 1, wherein the internal electrode is made  
from at least one selected from the group consisting of Al  
(4.28 eV), Ag (4.26 eV), Zn (4.33 eV), Nb (4.3 eV), Zr (4.05  
10 eV), Sn (4.42 eV), Ta (4.25 eV), V (4.3 eV), Hg (4.49 eV), Ga  
(4.2 eV), In (4.12 eV), Cd (4.22 eV), B (4.4 eV), Hf (3.9  
eV), La (3.5 eV), Ti (4.3 eV), Ca (2.87 eV), Mg (3.66 eV), Li  
(2.9eV), Na (2.75eV), K (2.3eV), Cs, (2.14eV), and alloys  
thereof.

15

6. The stacked organic light emitting device as  
claimed in claim 1, wherein each of the stacked light  
emitting sections has a light emission spectrum of a color  
selected from red, green, blue, and combination thereof, so  
20 that the stacked organic light emitting device is able to  
emit white light.

7. The stacked organic light emitting device as  
claimed in claim 1, wherein the stacked organic light  
25 emitting device is able to emit a white light of a wide range  
due to a micro-cavity effect.

8. A display apparatus comprising a stacked organic  
light emitting device as claimed in any one of claims 1 to 7.

30

1/4

FIG. 1






FIG. 2



2/4

FIG. 3



3/4

FIG. 4





FIG. 5



4/4

FIG. 6




FIG. 7





FIG. 8



## INTERNATIONAL SEARCH REPORT

International application No.  
PCT/KR2005/001001

## A. CLASSIFICATION OF SUBJECT MATTER

**IPC7 H05B 33/26**

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC7 H05B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched  
KR,JP : classes as above

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	JP 13-345180(SEMICONDUCTOR ENERGY LAB CO LTD) 14 DECEMBER 2001, See the whole document	1-8
A	JP 15-297575(TOYOTA CENTRAL RES & DEV LAB INC) 17 OCTOBER 2003, See the whole document	1-8
A	JP 09-232079(IDEMITSU KOSAN CO LTD) 05 SEPTEMBER 1997, See the whole document	1-8
A	JP 09-320763(IDEMITSU KOSAN CO LTD) 12 DECEMBER 1997, See the whole document	1-8
A	JP 09-129376(IDEMITSU KOSAN CO LTD) 05 MAY 1997, See the whole document	1-8

☐ Further documents are listed in the continuation of Box C.☒ See patent family annex.

\* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier application or patent but published on or after the international filing date

"I" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"Z" document member of the same patent family

Date of the actual completion of the international search

27 JULY 2005 (27.07.2005)

Date of mailing of the international search report

**09 AUGUST 2005 (09.08.2005)**

Name and mailing address of the ISA/KR

Korean Intellectual Property Office  
920 Dunsan-dong, Seo-gu, Daejeon 302-701,  
Republic of Korea

Facsimile No. 82-42-472-7140

Authorized officer

SEO, Jin Won

Telephone No. 82-42-481-5655



**INTERNATIONAL SEARCH REPORT**

Information on patent family members

International application No.

PCT/KR2005/001001

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
JP13345180	14. 12. 2001	JP13345180 JP2001345180A2 TW481931A US20010026846A1 US2001026846AA	14. 12. 2001 14. 12. 2001 01. 04. 2002 04. 10. 2001 04. 10. 2001
JP15297575	17. 10. 2003	JP15297575 JP2003297575A2	17. 10. 2003 17. 10. 2003
JP09232079	05. 09. 1997	JP09232079 JP9232079A2	05. 09. 1997 05. 09. 1997
JP09320763	12. 12. 1997	JP09320763 JP9320763A2	12. 12. 1997 12. 12. 1997
JP09129376	16. 05. 1997	JP09129376 JP9129376A2	16. 05. 1997 16. 05. 1997



**Family list**

6 application(s) for: **WO2006075822 (A1)**.

Sorting criteria: Priority Date Inventor Applicant Ecla

- 1 **Stacked organic light emitting device having high efficiency and high brightness**  
 Inventor: JUN-GI NOH JEOUNG-KWEN JEONG Applicant: LG CHEMICAL LTD [KR]  
 J [KR]  
 EC: H01L51/50E8; H01L51/52D10 IPC: H05B33/26; H05B33/26  
 Publication CN1947469 (A) - 2007-04-11 Priority Date: 2004-04-09  
 info: CN100493289 (C) - 2009-05-27
- 2 **STACKED ORGANIC LIGHT EMITTING DEVICE HAVING HIGH EFFICIENCY AND HIGH BRIGHTNESS**  
 Inventor: JEONG JI-WEON [KR]; LEE YOUNG-CHUL [KR] (+4) Applicant: LG CHEMICAL LTD [KR]; LG CHEMICAL LTD [KR]  
 EC: H01L51/50E8; H01L51/52D10 IPC: H05B33/26; H05B33/26  
 Publication EP1743508 (A1) - 2007-01-17 Priority Date: 2004-04-09  
 info:
- 3 **STACKED ORGANIC LIGHT EMITTING DEVICE HAVING HIGH EFFICIENCY AND HIGH BRIGHTNESS**  
 Inventor: Applicant:  
 EC: H01L51/50E8; H01L51/52D10 IPC: C09K11/06; H01L51/50; H05B33/12; (+7)  
 Publication JP2007533073 (T) - 2007-11-15 Priority Date: 2004-04-09  
 info:
- 4 **STACKED ORGANIC LIGHT EMITTING DEVICE HAVING HIGH EFFICIENCY AND HIGH BRIGHTNESS**  
 Inventor: JEONG JI WEON [KR]; LEE YOUNG CHUL [KR] (+4) Applicant: LG CHEMICAL LTD [KR]  
 EC: H01L51/50E8; H01L51/52D10 IPC: H05B33/26; H05B33/26  
 Publication KR20060001821 (A) - 2006-01-06 Priority Date: 2004-04-09  
 Info: KR100705256 (B1) - 2007-04-09
- 5 **Stacked Organic Light Emitting Device Having High Efficiency and High Brightness**  
 Inventor: JEONG JI W [KR]; LEE YOUNG C [KR] Applicant: (+4).  
 EC: H01L51/50E8; H01L51/52D10 IPC: H01L51/50; H01L51/50  
 Publication US2007221912 (A1) - 2007-09-27 Priority Date: 2004-04-09  
 info:
- 6 **STACKED ORGANIC LIGHT EMITTING DEVICE HAVING HIGH EFFICIENCY AND HIGH BRIGHTNESS**  
 Inventor: NOH JEOUNG-KWEN [KR]; JEONG JI-WEON [KR] (+4) Applicant: LG CHEMICAL LTD [KR]; NOH JEOUNG-KWEN [KR] (+5)  
 EC: H01L51/50E8; H01L51/52D10 IPC: H05B33/26; H05B33/26  
 Publication WO2006075822 (A1) - 2006-07-20 Priority Date: 2004-04-09  
 info:

Data supplied from the **espacenet** database — Worldwide